


NOKAN

An Engineering and Manufacturing Co.
www.nokanco.com



NK-DGZ-122

Zeolite 4A (Detergent Grade)

ITEM	INDEX
Appearance	White powder
Anhydrous builder content	78% Min
L.O.I (800 °C, 1h)	22% Max
Calcium exchange capacity (dry basis)	285 mg CaCO ₃ Min 160 mg CaO/g Min Typical: 185-196 mg CaO/g 330-350 mg CaCO ₃ /g
pH(5% In water , 25 °C)	11.5 Max
Bulk density	350-400 Kg/m ³
Particle Size (Mean diameter)	3-7 µm
Degree of whiteness (W=Y)%	98.5% Min
Al ₂ O ₃	26.5% Min

Tel: +98-21-22023563
Fax: +98-21-22023598
www.nokanco.com
E-mail: info@nokanprocess.com